

L4 ANSWER 45 OF 45 CAPLUS COPYRIGHT 2003 ACS
 AN 1972:515985 CAPLUS
 DN 77:115985
 TI Surface treatment of polyester synthetic fiber products
 IN Date, Yoshikazu; Wada, Masahiro
 PA Toyo Spinning Co., Ltd.
 SO Jpn. Tokkyo Koho, 5 pp.
 CODEN: JAXXAD
 DT Patent
 LA Japanese
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 47002512	B4	19720124	JP 1969-4950	19690123 <--
AB	<p> A copolymer derived from terephthalic acid, ethylene glycol, and polyethylene glycol with or without isophthalic acid was stably dispersed in water with polyethylene glycol alkylphenyl monoether sulfate, and the dispersion was applied to a polyester textile at pH 2-6 and >70.deg. to give the textile antistatic properties. Thus, a poly(ethylene terephthalate-isophthalate) textile was immersed 1 hr in a mixture of 6 g/l. 15% dispersion of terephthalic acid-isophthalic acid-ethylene glycol-polyethylene glycol block copolymer and 0.1 g/l. hexaethylene glycol p-nonylphenyl ether ammonium sulfate [36507-98-9] at pH 3 (adjusted with AcOH) and 95.deg., dried, and heated 30 sec at 140.deg.. The textile had elec. resistances before and after 5 washings 6 .tim. 107 and 1 .tim. 109 Ω, resp., compared with >1012 Ω for a similar untreated textile. </p>				

BEST AVAILABLE COPY